

# SIBRALIT DX

Intumescent fire protection filler.

Subject to errors, typographical errors and modifications. The specified details reflect the state of the art / the effective standard at the time of printing (09/2014). Please let us know when you need information about the legal and technical requirements or the manufacturer's specification that apply to your specific case. © Copyright svt Unternehmensgruppe, Seevetal  
PYRO-SAFE is a registered trademark © of svt Unternehmensgruppe, Seevetal.



## Product description

### Fields of application

Intumescent fire protection filler on water-based dispersion for indoor use. Approved product for cable, pipe and combined penetration sealings.

### Product features

Solvent-free and non halogen.

### Fire rating of systems

Up to 2 hours

### Applicability certificate

Tested and approved according to national and international standards as e.g.:  
DIN, other standards on request

Pipes

Cables

## Technical Data

---

### Handling

- The surface has to be dry, dust-free und free of grease
- The application is done by filling
- The consumption depends on the size of the opening

### Ordering information

310 ml cartridge

### Storage

Protect the product from frost!

Cool and dry (+5 °C up to +25 °C).

### Safety instructions

Please refer to our MSDS (safety data sheet).

### Technical data

Colour	white
Density (+ 20 °C)	1.20 - 1.38 g/cm <sup>3</sup>
Viscosity (+ 20 °C)	paste-like
Volatile content	< 140 g/l
Drying time (at +23°C / 65% ± 3% rel. humidity)	Dust dry: min. 8 hours Thoroughly dry: min. 10 days (depends on film thickness)
Processing temperature	+5 °C up to +25 °C

### Applied systems

---

- PYRO-SAFE Novasit
- PYRO-SAFE Universal
- PYRO-SAFE Bag
- PYRO-SAFE Pipe seals for combustible pipes
- PYRO-SAFE Pipe seals for non-combustible pipes